



## BONROY INTERNATIONAL LIMITED.

ZIBO NEW MATERIAL TRADING CENTER, PLAZA A,  
NORTHEASTREN CORNER OF BEIJING ROAD AND  
RENMIN ROAD, ZHANGDIAN, ZIBO, SHANDONG, P.R.  
CHINA.

TEL: 0086-533-8170985

[www.bonroy-int.com](http://www.bonroy-int.com)

## TECHNICAL DATA SHEET

### BINDER® L-2510

**BINDER® L-2510** is liquid C5 tackifying resin with low color and very narrow molecular weight distribution. It displays excellent compatibility with polymers, enhances tack, improves flexibility, and improves low temperature properties.

L-2510 used in PSA can avoid process oil migration in lower temperature since its low Tg.

It's excellent low temperature properties assure PSA maximum performance and long shelf-life.

#### SUGGEST APPLICATION

Low temperature label such as fruits & vegetables label, vaccines & blood bottle label etc..

Tire label & mouse trap adhesive etc. which adhesive surface had exposed to air.

Sealants

#### SPECIFICATIONS

Softening Point (Ring & Ball, °C)	7-9	ASTM E 28
Initial Color (Yellow Index )	45 Max	ASTM D 6166
Wax Cloud Point (EVA/Resin/Wax=30/45/25)	75 Max	BDTM/Q-10

#### TYPICAL PROPERTIES

Softening Point (Ring & Ball, °C)	8	ASTM E 28
Initial Color (Yellow Index )	35	ASTM D 6166
Wax Cloud Point (EVA/Resin/Wax=30/45/25)	70	BDTM/Q-10
Acid Value (KOH mg/g)	0.1	ASTM D 974
Melt Viscosity BRF, @40°C, cps	24,600	ASTM D 3236
Molecular Weight (G.P.C, Mn)	550	
(G.P.C, Mw)	600	
(G.P.C, Mz)	650	
D	1.1	

#### PACKING

**BINDER® L-2510** is available both in 170Kg galvanized iron drum and 900 KGS standard IBC drums.

#### STORAGE

**BINDER® L-2510** should be stored in cool ventilated dry place. Recommended temperature no exceeding 35°C.